

# **Technical Data Sheet**

## Bondloc B270 Studlock (Threadlocker)

#### PRODUCT DESCRIPTION

B270 Studlocker is a permanent green coloured general purpose adhesive for permanent threaded assemblies. B270 locks studs up to 1", sealing against leakage and corrosion. It is chemical resistant, resisting fuels, lubricants and most industrial liquids and gases.

## **APPLICATIONS**

B270 Studlocker eliminates double nutting and/or welding of critical assemblies. Using B270 Studlocker permits reduced casting thickness and ultimate lightness, reduced assembly stress and eliminates cracked castings due to interference fit stresses.

#### **USEFUL NOTES**

Using B270 Studlocker is easy, it is colour coded green to assist in selection. Because of its chemical resistance it is ideal in applications such as a sealant for refrigeration plant, air conditioning, big plant and process equipment using corrosive chemicals.

## **INSTRUCTIONS FOR USE**

Ensure parts are clean, dry and free from oil and grease.

#### PROCEDURE FOR APPLICATION

Product is normally hand applied from the bottle.

#### COMPATIBILE ACCELERATORS/PRIMERS

Primers such as B7471 (Standard Anaerobic Activator) or the faster B7649 Structural Accelerator

#### **STORAGE**

Store in a cool area out of direct sunlight. Shelf Life >18 months at 20°C.

### **TECHNICAL FEATURES**

| Resin                                   | Dimethacrylate   |
|---|------------------|
| Colour                                  | Green            |
| Cure speed with<br>Activator            | 5 minutes        |
| Cure speed without<br>Activator         | 10 minutes       |
| Viscosity Brookfield<br>Sp3 @20rpm@25°C | 500 cps          |
| Max Thread Size                         | M80              |
| Flash Point                             | >100°C           |
| Shelf Life                              | 18 months @ 20°C |
| Specific Gravity                        | 1.06             |
| Temperature Range                       | -55°C to +180°C  |

#### **TYPICAL BOND CHARACTERISTICS**

| Full Cure Time                          | 12 hours          |
|---|-------------------|
| Cure time with good % of final strength | 2 hours           |
|   |                   |
| Range of Strength -                     |                   |
| Breakaway                               | 33N.m             |
| Prevailing                              | 33N.m             |
| Trevailing                              | 3314.111          |
| DIN 54454 Breakloose:                   | 25N.m max 55N.m   |
|   |                   |
| DIN 54454 Prevailing:                   | 45N.m up to 70N.m |
|   |                   |

## **HEALTH & SAFETY**

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

## **PACKAGING FORMAT**

Bottles......10ml,25ml,50ml, 250ml Clam Packs......10ml, 25ml, 50ml

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondioc are subject to terms and conditions set out in the contract. Bondioc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondioc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondioc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

